

# DuPont™ Krytox® EG Electronic Grade Greases

## Product Data

### Typical Properties\* of Krytox® Electronic Fluorinated Greases

Electronic Grease Grade	EG 2000	EG 3000
Viscosity of Base Oil, cSt D-445 at 20 °C (68 °F) at 38 °C (100 °F) at 99 °C (210 °F) at 204 °C (400 °F)	800 270 26 3.9	1600 500 43 6.0
Vapor Pressure of Base Oil Knudsen at 38 °C (100 °F) torr at 260 °C (500 °F) torr	$8 \times 10^{-8}$ $2 \times 10^{-3}$	$6 \times 10^{-9}$ $3 \times 10^{-4}$
Volatility of Base Oil D-972 (Mod) wt% loss in 22 hr at 149 °C (300 °F) at 204 °C (400 °F) at 260 °C (500 °F)	— 1 6	— — 3
Pour Point of Base Oil D-97 °C °F	-35 -30	-30 -20
Texture	Buttery	Buttery
Penetration ASTM D-217 60 Strokes	265–295	265–295
Mechanical Stability ASTM D-217 10,000 St 100,000 Strokes	No change from original grade	No change from original grade
Oxidation Stability ASTM D-942 99 °C (210 °F)	0 psig O <sub>2</sub> pressure drop after 600 hr	0 psig O <sub>2</sub> pressure drop after 600 hr
Liquid Oxygen Impact ASTM D-2512, NASA MSFC 106B	Pass	Pass
Grease Density, g/ml 25 °C (77 °F)	1.93	1.93
Oil Separation FTMS 791B 321.1 wt% loss in 30 hr at 99 °C (210 °F) at 204 °C (400 °F)	3 11	3 10
Evaporation FTMS 791B 350.1 wt% loss in 22 hr at 99 °C (210 °F) at 204 °C (400 °F) at 260 °C (500 °F)	— 1 6	Not Tested 1 6
Estimated Useful Range °C °F	-34 to 288 -30 to 550	-29 to 316 -20 to 550+

\*This table gives typical properties (not specifications) based on historical production performance. Viscosity may vary within ±10%. DuPont does not make any express or implied warranty that these products will continue to have these typical properties.

All standard grades of grease are thickened with Krytox® 2000 polytetrafluoroethylene PTFE, whose formula is (CF<sub>2</sub>-CF<sub>2</sub>)<sub>n</sub>. This special high efficiency thickener has a melting point of 325 °C (617 °F) and has low molecular weight and submicron (.2 μm) particle size for higher performance in bearings.

Krytox® EG series greases are white buttery greases with all of the same properties as the 143 series oils that they are made from, but they are in grease form.



The miracles of science™

# DuPont™ Krytox® EG Electronic Grade Greases

For more information or technical assistance,



TMC Industries, Inc.  
1423 Mill Lane, Waconia, MN 55387  
800-772-8179 / 952-442-1140  
sales@tmcindustries.com  
www.tmcindustries.com

Copyright © 2008. The DuPont Oval, DuPont®, The miracles of science™, and Zony® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

The information set forth herein is furnished free of charge and based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own risk. Because conditions of use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be taken as license to operate under or a recommendation to infringe any patents.



*The miracles of science™*